

PRODUCT DESCRIPTION

General Information	It is a Polyester based two component multifunctional putty with high filling power developed to hide, fill scratches and cavities on surfaces.
Application areas	Buses, Trucks, Taxi like motor vehicles. Machineries. Manufacturing machineries. Wind turbines.
Properties	With its high filling effect, it easily fills the surface cavities. Easy application and sanding. It doesn't create pores. It doesn't cause sandpaper clogging.

COMPONENTS AND ADDITIVES

Hardener

Polyester Putty Hardener (Peroxide)

APPLICATION DETAILS

Application Method



Steel Spatula

Drying Time



at 20°C 20-25 minutes

Surface Preparation



Dusts, rust, oil, dirt should be cleaned from surfaces before application.

Recommended Sanding(Dry)



P80 / P150 / P180 / P220 / P360 / P400

CAUTION



No product should be applied before a surface check is done.

The heat released while fiberglass putty is drying can damage not fully dried paints.

Not more than 3% of hardener should be used, more than that may lead to peroxide spillage.

Damage assessment cloth should be used before and after application of polyester putty.

MIXING RATIO (by volume)

	Product	100 unit
	Hardener	2-3 unit
	Mixture Usege Life	4-5 minutes

EQUIPMENT

Protection



It is recommended to use appropriate personal protective equipment during application.

SHELF LIFE



Unopened packing can stay minimum 1 year at room temperature.



TECHNICAL DATA SHEET

POLYESTER PUTTY

PACKING TYPES

0.970 Kg / 1.8 Kg / 2.7 Kg / 3 Kg

HEALTH AND SAFETY DATA



Please follow the instruction mentioned on packs. Users should destroy the wastages according to the standards of health and safety regulations. For more information check the Material Safety Data Sheet.

The technical information contained in this sheet was prepared according to our applications, past experiences, and laboratory tests. Our company is not responsible for applications done outside the stated conditions and application errors that occur due to the user.

Sintaş Boya ve Kimya Sanayi A.Ş.

Tel: +90 282 725 25 35 (Pbx), Fax: +90 282 725 25 34
info@sintas.com.tr , www.sintas.com.tr

